

## ELIX ABS-3D FC

USP class VI Biocompatible & Food Contact ABS material optimized for FDM 3D-printing technology

---

### **Major Benefits**

- Easy printability
- Excellent feature definition and surface finish
- Low emission and odor grade
- Biocompatible: ISO 10993-1 USP Class VI
- Food contact approved material acc. EU No 10/2011<sup>1</sup> and 21 CFR FDA

### **Chemical composition**

Acrylonitrile-butadiene-styrene (ABS) copolymer

### **Physical form**

White to slightly yellowish pellets.

### **3D printing material properties**

<b>Properties</b>	<b>Values</b>
<i>Flowability</i>	<i>Medium</i>
<i>Heat Resistance</i>	<i>Medium</i>
<i>Strength</i>	<i>Medium</i>
<i>Warping</i>	<i>Standard</i>
<i>Resolution</i>	<i>Good</i>

**ABS General properties**

<b>Properties</b>	<b>Test condition</b>	<b>Unit</b>	<b>Standard</b>	<b>Value</b>
<b>Rheological properties</b>				
Melt Volume- flow Rate	220°C, 10 Kg	cm <sup>3</sup> /10'	ISO 1133	18
<b>Mechanical Properties (23°C /50% H.R.)</b>				
Yield Stress	50 mm/min	MPa	ISO 527-1,2	47
Elongation at Break	1 mm/min	%	ISO 527-1,2	16
Tensile modulus	1 mm/min	MPa	ISO 527-1,2	2450
Flexural modulus	2 mm/min	MPa	ISO 178	2500
Izod notched impact strength	23 °C	KJ/m <sup>2</sup>	ISO 180-1A	14
Izod notched impact strength	- 30 °C	KJ/m <sup>2</sup>	ISO 180-1A	7
Ball Indentation Hardness		N/mm <sup>2</sup>	ISO 2039-1	120
<b>Thermal properties</b>				
Vicat softening temperature	B50, 50 °C/h	°C	ISO 306	97
Burning behavior UL 94	1.6 mm	Class	UL94	HB
<b>Other properties</b>				
Density	25°C	g/cm <sup>3</sup>	ISO 1183-1	1.06

<b>Processing conditions for 3D printing</b>	<b>Value</b>
Temperature resistance	97 °C
Slumping temperature	107 °C
Printing temperature	230 – 250 °C
Recommended printbed temperature	80 – 100 °C

---

### ***Disclaimer for sales products***

#### Disclaimer for sales products

This information and our technical advice - whether verbal, in writing or by way of trials - are given in good faith but without warranty, and this also applies where proprietary rights of third parties are involved. Our advice does not release you from the obligation to verify the information currently provided –especially that contained in our safety data and technical information sheets– and to test our products as to their suitability for the intended processes and uses. The application, use and processing of our products and the products manufactured by you on the basis of our technical advice are beyond our control and, therefore, entirely your own responsibility. Our products are sold and our advisory service is given in accordance with the current version of our General Conditions of Sale and Delivery.

#### Test values

Unless specified to the contrary, the values given have been established on standardised test specimens at room temperature. The figures should be regarded as guide values only and not as binding minimum values. Kindly note that, under certain conditions, the properties can be affected to a considerable extent by the design of the mould/die, the processing conditions and the colouring.

#### Processing note

Under the recommended processing conditions small quantities of decomposition product may be given off during processing. To preclude any risk to the health and well-being of the machine operatives, tolerance limits for the work environment must be ensured by the provision of efficient exhaust ventilation and fresh air at the workplace in accordance with the Safety Data Sheet. In order to prevent the partial decomposition of the polymer and the generation of volatile decomposition products, the prescribed processing temperatures should not be substantially exceeded. Since excessively high temperatures are generally the result of operator error or defects in the heating system, special care and controls are essential in these areas.

ELIX Polymers, S.L. - E-43006 Tarragona

---

Edition 23.01.17

[info@elix-polymers.com](mailto:info@elix-polymers.com)